



TEST THERMIQUE SECONDAIRE

CAPACITÉS DE PRODUCTION									
Épaisseurs		Dimensions minimales		Dimensions maximales*		Poids		Tolérances dimensionnelles	
mm	po	mm	po	mm	po	kg/m ²	lb/pi ²	mm	po
3	1/8	102 x 229	4 x 9	1499 x 2286	59 x 90	7.86	1.61	±1.6	±1/16
4	5/32	102 x 229	4 x 9	1778 x 2794	70 x 110	9.91	2.03	±1.6	±1/16
5	3/16	102 x 229	4 x 9	2286 x 3810	90 x 150	11.96	2.45	±1.6	±1/16
6	1/4	102 x 229	4 x 9	2794 x 5182	110 x 204	14.60	2.99	±1.6	±1/16
8	5/16	102 x 229	4 x 9	2794 x 5182	110 x 204	20.02	4.10	±2.0	±5/64
10	3/8	102 x 229	4 x 9	2794 x 5182	110 x 204	23.97	4.91	±2.4	±3/32
12	1/2	102 x 229	4 x 9	2794 x 5182	110 x 204	31.54	6.46	±3.2	±1/8
15	5/8	102 x 229	4 x 9	2438 x 4978	96 x 196	39.40	8.07	±4.0	±5/32
19	3/4	102 x 229	4 x 9	2438 x 4978	96 x 196	47.31	9.69	±4.8	±3/16

* Certaines conditions peuvent s'appliquer, contactez-nous pour plus de détails.